

INOFLAR® 2010

TECHNICAL DATA SHEET

TECHNICAL INFORMATION

INOFLAR® 2010 is a flexible low molecular weight granular PVDF copolymer resin suitable for molding and extrusion applications.

PRODUCT FEATURES

- Low temperature flexibility
- Excellent chemical resistance
- High temperature resistance
- Good thermal & mechanical performance
- Easy processability

TYPICAL PROPERTIES*

Physical Unit	Unit	Value	Test Method
Specific Gravity	-	1.76 – 1.79	ASTM D792
Water Absorption	%	< 0.04	ASTM D570
Rheological			
Melt Mass Flow Rate (230 °C, 5 Kg Load)	g/10min	10 – 20	ASTM D1238
Mechanical#			
Tensile Modulus	MPa	600 – 1200	ASTM D638
Tensile Strength (Yield)	MPa	25 – 35	ASTM D638
Tensile Strength (Break)	MPa	30 – 50	ASTM D638
Tensile Elongation (Yield)	%	10 – 20	ASTM D638
Tensile Elongation (Break)	%	> 300	ASTM D638
Flexural Modulus (Break)	MPa	600 - 800	ASTM D790
Flexural Strength @5% Strain	MPa	20 - 35	ASTM D790
Impact			
Charpy Notched Impact Strength (23 °C)	J/m	No Break	ASTM D256
Hardness			
Durometer Hardness (Shore D, 1 sec, 2.00 mm)	-	65 – 70	ASTM D2240



Inoflar® PVDF resins are manufactured without the use of Fluoro-surfactants

INOFLAR® 2010

Thermal			
Glass Transition Temperature (10 °C/min)	°C	-40	ASTM D4065
Melting Temperature	°C	158 – 165	ASTM D3418
Deflection Temperature under load (1.80 MPa)	°C	40 – 55	ASTM D648
Flammability			
Oxygen Index	%	42	ASTM D2863

PACKAGING

INOFLAR® 2010 pellets are available in 25 kg multilayered bags, packed in a polyethylene liner.

HANDLING AND STORAGE

INOFLAR® 2010 presents no safety hazard under normal handling conditions. Please refer to the material safety data sheet to avoid potential hazards prior to processing.

INOFLAR® is the brand name of Gujarat Fluorochemicals Limited (GFL) used for its brand of fluoropolymer resin. INOFLAR® can be used in applications duly approved by GFL. Customers who plan to use the word INOFLAR® as the trademark on or relation to their fluoropolymer parts and other products in any style or combination or any manner whatsoever must contact GFL for prior permission for such use. No consumer/user of GFL fluoropolymer resin is permitted to claim that their products contain INOFLAR® without prior permission from GFL.

The information provided in the bulletin is furnished at no cost to the recipient and is based on the information and technical data that Gujarat Fluorochemicals Limited believes is correct and sound. Those who choose to use the information must be technically qualified, and do so entirely at their own cost and risk. The users must determine and ensure that their specific conditions of processing present no health or safety hazards. GFL does not warranty, either expressly or impliedly in respect of the use of this information for application of its INOFLAR® branded fluoropolymer resin and shall bear no liability as a result of any loss or damage caused directly or indirectly due to use of any information provided in this bulletin. Nothing contained herein can be taken or construed as a grant of license by GFL to operate under or a recommendation to infringe any patents.

SALES AND TECHNICAL SUPPORT

Corporate & Marketing office:

Gujarat Fluorochemicals Limited

Inox Towers, Plot no. 17, Sector 16/A

Noida-202301, U.P., INDIA

Tel: +91-120-6149600

Fax: +91-120-6149610

Europe

Gujarat Fluorochemicals GmbH

Esplanade 40, 9th Floor

20354 Hamburg, Germany

+49 040 5582 395- 80

Works

Gujarat Fluorochemicals Limited

12/A, GIDC Dahej Industrial Estate.

Tehsil- Vagra, Distt. Bharuch-392230, Gujarat, INDIA

Website: www.fluonox.co.in; www.gfl.co.in

Email: contact@gfl.co.in

Americas

GFL Americas, LLC

1212 Corporate Dr., Suite-540,

Irving, TX 75038, USA

+1 512 446 7700

