

## INOFLAR™ 1150

### TECHNICAL DATA SHEET

#### TECHNICAL INFORMATION

INOFLAR™ 1150 is a very high molecular weight PVDF homopolymer resin in powder form suitable for use as binders in batteries.

#### PRODUCT FEATURES

- High viscosity
- Excellent chemical resistance
- Good thermal & mechanical performance
- Excellent electrochemical stability

#### TYPICAL PROPERTIES

Physical	Unit	Value	Test Method
Specific Gravity	-	1.76 – 1.79	ASTM D792
<b>Rheological</b>			
Melt Viscosity (230 °C, 100 S <sup>-1</sup> )	kPoise	45 – 55	ASTM D3835
<b>Mechanical</b>			
Tensile Strength (Yield)	MPa	40 – 55	ASTM D638
Tensile Strength (Break)	MPa	35 – 45	ASTM D638
Tensile Elongation (Break)	%	>50	ASTM D638
<b>Thermal</b>			
Melting Temperature	°C	158 – 165	ASTM D3418
<b>Flammability</b>			
Oxygen Index	%	44	ASTM D2863

#### PACKAGING

INOFLAR™ 1150 powder is available in 25 Kg plastic drums, packed in a polyethylene liner.

#### HANDLING AND STORAGE

INOFLAR™ 1150 presents no safety hazard under normal handling conditions. Please refer to the material safety data sheet to avoid potential hazards prior to processing.

INOFLAR™ is the brand name of Gujarat Fluorochemicals Limited (GFL) used for its brand of fluoropolymer resin. INOFLAR™ can be used in applications duly approved by GFL. Customers who plan to use the word INOFLAR™ as the trademark on or relation to their fluoropolymer parts and other products in any style or combination or any manner whatsoever must contact GFL for prior permission for such use. No consumer/user of GFL fluoropolymer resin is permitted to claim that their products contain INOFLAR™ without prior permission from GFL.

The information provided in the bulletin is furnished at no cost to the recipient and is based on the information and technical data that Gujarat Fluorochemicals Limited believes is correct and sound. Those who choose to use the information must be technically qualified, and do so entirely at their own cost and risk. The users must determine and ensure that their specific conditions of processing present no health or safety hazards. GFL does not warranty, either expressly or impliedly in respect of the use of this information for application of its INOFLAR™ branded fluoropolymer resin and shall bear no liability as a result of any loss or damage caused directly or indirectly due to use of any information provided in this bulletin. Nothing contained herein can be taken or construed as a grant of license by GFL to operate under or a recommendation to infringe any patents.

## SALES AND TECHNICAL SUPPORT

**Corporate & Marketing Headquarter**  
**Gujarat Fluorochemicals Limited INOX**  
Towers, 17 , Sector-16A,  
Noida - 201301 U.P., India  
+91 120 6149600

**Europe**  
**Gujarat Fluorochemicals GmbH**  
Regus Center Watermark 14<sup>th</sup> Floor,  
Überseeallee 10, 20457 Hamburg, Germany  
+49 40 808074-667/668

**Works**  
**Gujarat Fluorochemicals Limited**  
12/A Dahej, GIDC, Industrial Estate,  
Tehsil Vagra, Dist. Bharuch 392130, Gujarat, India  
+91 2641 618003

**Americas**  
**GFL Americas, LLC**  
1212 Corporate Dr., Suite-  
540, Irving, TX 75038, USA  
+1 512 446 7700

